



Subtle greys

PANAGET

manufacture française de parquet
DEPUIS 1929



No 1007655

FRENCH OAK ZENITUDE FLANELLE, HERRINGBONE 139 TONGUE & GROOVE / 14 MM

Characteristics

Species: French oak **Origin:** France

Grading: Zenitude - light and dark wood, black knots, filled knots, opened knots, discolouration, cracks, splits, sapwood. Grade with all peculiarities of the wood without limitation. The size of the knots is proportional to the width of the planks.

Finish: Flanelle - brushed, grey-brown-tone matt oiled / Hard wax oil

For oiled wood floors, apply a thin coat of Panaget maintenance oil right after installation. Please refer to our maintenance guide. While we take the greatest care in manufacturing our flooring, there can sometimes be slight variations in colouring. So it's important to factor in margin of 2-5% more than the actual surface you're covering. This means you won't run out of planks and you will be sure to enjoy a beautiful finished product.

Design

Engineered single plank, herringbone made under the patent EN 13489
Tongue & Groove



Description

Width: 139 mm

Length: 800 mm

Thickness: 14 mm

Top layer: 3.4 mm

Core: plywood

Counterbalance: unrolled wood

Profile: 4 bevels with 2 aged

Packing

Sqm/-pack: 2.22

Pack/pallet: 32

Sqm/pallet: 71.04

Weight/sqm: 7.4 kg

Weight/pallet: 525.7 kg

Installation method




Floating glued
installation under the
patent DTU 51.11



Glue down installation
under the patent DTU 51.2



Floating installation using
plastic DPM and Isol 20 or fully
glue down using Presto PM





DECLARATION OF PERFORMANCE

NO 1007655

Unique identification code of the product-type: Herringbone 139 Tongue & Groove, 14 mm, French oak

Intended use/es: Engineered single plank, herringbone made under the patent EN 13489

Floating glued installation under the patent DTU 51.11

Manufacturer: PANAGET - 3 rue d'Orgères 35230 Bourgbarré / FRANCE

System/s of Assessment and Verification of Constancy of Performance: No4

Harmonised standard: EN 14342 : 2013

Declared performances:

| Essential features | Performances | Appropriate Technical Documentation and/or Specific Technical Documentation |
|---|-----------------------------------|---|
| Reaction to fire | Dfl-s1 | EN 14342 : 2013 |
| Features for this classification: - Average minimum density (Kg/m ³) - Average thickness (mm) - Intended use, fitting mode | 500 14 Floating fit | |
| Formaldéhyde emission | E1 | |
| Content of pentachlorophénol | PCP ≤ 5 ppm | |
| Release of other dangerous substances: - VOC* emissions (Decree No 2011-321) - CMR 1&2** emissions (Decree No DEVP0910046A) | Classe A+ < 1µg/m ³ | ISO 16000 |
| Breaking strength | N/A | - |
| Slipperiness | N/A | - |
| Thermal conductivity (W/m.K) | 0.13 | EN 14342 / Chapter 4.7 |
| Thermal resistance (m ² .K/W) | 0.108 | |
| Biological sustainability | Classe 1 | EN 335 |

N/A: Not Applicable

*VOC: Volatile Organic Compounds

**CMR 1&2: Carcinogenics, Mutagens or Reproductive toxin of 1 and 2 category

The performance of product identified above is in conformity with the set of declared performance/s. This declaration of performance is issued, in accordance with Regulation (EU) No 305/2011. under the sole responsibility of the manufacturer identified above.

Signed for and behalf of the manufacturer by: Carole FRANÇOIS - Executive Director

Bourgbarré, 12 november 2019

Carole FRANÇOIS

3 rue d'Orgères - 35230 Bourgbarré - FRANCE / tel: +33 (0)2 99 05 77 77 - fax: +33 (0)2 99 57 73 55

Entreprise dont le système qualité a été **certifié ISO 9001** par Bureau Veritas Certification.

SAS au capital de 4 957 200 € - RCS Rennes B 402 853 220 - Siret : 402 853 220 000 34 - APE : 1622 Z - No TVA : FR 0640 2853220

www.panaget.com