



Subtle greys

PANAGET

manufacture française de parquet
DEPUIS 1929



N° 1022770

FRENCH OAK CLASSIC/AUTHENTIC CAFÉ CRÈME, HERRINGBONE 90 TONGUE&GROOVE / 12 MM

Characteristics

Specie: French oak **Origin:** France

Grade: Classic/Authentic - Light and dark wood, black knots, filled knots, partially opened knots, black marks, medular rays, traces of discolouration.

Finish: Café crème - brushed, coffee latte tone matt lacquered / Ecostrong matt lacquer - Gloss: 4/6

Design

Engineered single plank herringbone made under the patent EN 13489
Tongue&Groove



Description

Width: 90 mm

Length: 590 mm

Thickness: 12 mm

Top layer: 2.5 mm

Core: HDF*

Counterbalance: unrolled wood

Profile: 4 bevels

*High Density Fiber board

Packaging

sqm/pack: 1.91

Pack/pallet: 32

sqm/pallet: 61.12

Weight/sqm: 9.9 kg

Weight/pallet: 605.1 kg



Installation method



Floating glued
installation under the
patent DTU 51.11





Glue down installation
under the patent DTU 51.2



Floating installation gluing TG
using plastic DPM and Isol 20 or
fully glue down using Presto PM



Fully glue down Presto PM



PANAGET - 3 rue d'Orgères - 35230 Bourgbarré - FRANCE
tel: +33 (0)2 99 05 77 77 // fax: +33 (0)2 99 57 73 55 // www.panaget.com

DECLARATION OF PERFORMANCE

N° 1022770



Unique identification code of product-type: Herringbone 90 Tongue&Groove, 12 mm, French oak

Intended use/es: Engineered single plank made under the patent EN 13489

Floating glued installation under the patent DTU 51.11

Manufacturer: PANAGET - 3 rue d'Orgères 35230 Bourgbarré / FRANCE

System/s of Assessment and Verification of Constancy of Performance: n°4

Harmonised standard: EN 14342 : 2013

Declared performances:

Essential features	Performances	Appropriate Technical Documentatio and/or Specific Technical Documentation
Reaction of fire	Dfl-s1	EN 14342 : 2013
Features for this classification: - Average minimum density (Kg/m ³) - Average thickness (mm) - Intended use, fitting mode	500 12 Floating fit	
Formaldehyde emission	E1	
Content of pentachlorophenol	PCP ≤ 5 ppm	
Release of other dangerous substances: - VOC* emissions (Decree No 2011-321) - CMR 1&2** emissions (Decree No DEV0910046A)	Class A+ < 1µg/m ³	ISO 16000
Breaking strength	N/A	-
Slipperiness	N/A	-
Thermal conductivity (W/m.K)	0.15	EN 14342 / Chapter 4.7
Thermal resistance (m ² .K/W)	0.080	
Biological sustainability	Class 1	EN 335
RE2020 - Building Carbon Index	3 kg.CO ₂ /m ²	-
FDES 2022 - Life Cycle impact assessment	8.6 kg éq. CO ₂ /m ²	-

N/A : Not Applicate

*VOC: Volatile Organic Compounds

**CMR 1&2: Carcinogenics, Mutagens or Reproductive toxin of 1&2 category.

The performances of product identified above is in conformity with the set of declared performance/s. This declaration of performance is issued, in accordance with Regulation (EU) No 305/2011 under the sole responsibility of the manufacturer identified above.

Signed for and behalf of the manufacturer by: Carole FRANÇOIS - Executive Director

Bourgbarré, January 27th 2025
Carole FRANÇOIS

3 rue d'Orgères - 35230 Bourgbarré - FRANCE / tel: +33 (0)2 99 05 77 77 - fax: +33 (0)2 99 57 73 55

Entreprise dont le système qualité a été **certifié ISO 9001** par Bureau Veritas Certification.

SAS au capital de 4 957 200 € - RCS Rennes B 402 853 220 - Siret : 402 853 220 000 34 - APE : 1622 Z - n° TVA : FR 0640 2853220

www.panaget.com